



✓ Zerust® AxxaClean™ 3048

Zerust® AxxaClean™ 3048 is a fast-acting rust and tarnish remover. It rapidly removes medium to heavy corrosion even in cracks and crevices. Cleaned surfaces are free of black-carbon residue and resistant to flash-corrosion.

Zerust® AxxaClean™ 3048 cleans ferrous metals, brass, copper and various alloys of rust and tarnish. AxxaClean™ 3048 is available in two formulas; immersion and a brush-on gel. Surfaces properly cleaned with Zerust® AxxaClean™ 3048 are protected from flash-rust or re-tarnishing for several days in a controlled environment. Cleaned and dried items can be immediately painted or welded.

For optimum results, after cleaning with AxxaClean™ 3048, rinse with a solution of AxxaVis™ PX-05AN acid neutralizer and dry thoroughly with filtered compressed air. For corrosion prone metals such as cast iron, use a Zerust® Axxanol™ or Axxatec™ rust preventative coating or VCI packaging product. AxxaClean™ 3048 has a pH between 0.5 and 1.5. The product may attack paints, zinc and galvanized coatings. Test product before use. Use Zerust® AxxaClean™ 2048 if a less acidic product is needed.

Application Example

AxxaClean™ 3048 is designed to rapidly remove even heavy corrosion and reduce required dwell time of product.



▶ Benefits

Rapidly removes heavy rust and tarnish

Inhibits flash corrosion on treated surfaces

No VOC's, CFC's, silicones or heavy metals

Does not leave staining or dark carbon residues

Cleaned metals are ready to be painted or welded

Complementary Products

Zerust® VCI Packaging and Diffusers
Axxatec™ Water-Based RPs
Axxanol™ Oil-Based RPs
AxxaVis™ Additives
AxxaWash™ Cleaners



AxxaClean™ 3048 comes in immersion and brush-on formulations.

Technical Data

Comparison of Zerust® AxxaClean™ Rust Remover Series

Attributes	AxxaClean™ ICT®620-RR	AxxaClean™ 2048	AxxaClean™ 3048
Corrosion Removal Power	Light to medium rust, even in cracks and crevices	Medium corrosion, even in cracks and crevices	Heavy corrosion, even in cracks and crevices
Speed	Slow	Moderate	Rapid
Metals Treated	Ferrous	Ferrous, brass, copper	Ferrous, brass, copper
Application Methods	Immersion	Immersion, Brush-on, Spray	Immersion, Brush-on
pH Level	Neutral pH of about 7	Mild acidic pH of about 2.5	Stronger acidic pH between 0.5-1.5
Temperature For Use	70°F (21°C) or above	70°F (21°C) or above	40°F (4°C) or above
Compatibility (<24 hour soak)	Safe for metals*, paint, gaskets, rubber, plastics	Safe for metals*, paint, gaskets, rubber, plastics	May attack soft metals*, some paints and coatings
Post-Cleaning Action	Do not let product dry on surface. Recommended DI or RO water rinse. Wipe off and dry well.	Do not let product dry on surface. Recommended DI or RO water rinse. Wipe off and dry well.	Do not let product dry on surface. Recommended DI or RO water rinse. Wipe off and dry well.
Corrosion Protection	Additional corrosion protection needed	Provides flash-corrosion protection in controlled environments	Provides flash-corrosion protection in controlled environments
Shelf Life and Handling	2 years from date of shipment when stored out of sunlight and in original packaging.	2 years from date of shipment when stored out of sunlight and in original packaging.	2 years from date of shipment when stored out of sunlight and in original packaging.

*Test before use on zinc and cadmium. Check with your Zerust® technical representative for details.

DECLARATION

This Data sheet and information it contains is considered to be accurate at the date of printing. No representation or warranty, expressed or implied is made as to the accuracy or completeness of the data and information contained in this publication. It is the User's obligation to evaluate and use products safely and within the scope advised in the data sheet and to comply with all applicable laws and regulations.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on validations and tests conducted by Northern Technologies International Corporation/Zerust® or its partners and are believed to be reliable, but the accuracy or completeness thereof is not guaranteed. We warrant our products will be free from defects when shipped to customer. Our obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Northern Technologies International Corporation/Zerust® or its partners or agent of the claimed defect within 3 months after shipment of product to customer. Customer shall pay all freight charges for replacement products. We shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products. And any financial claims shall be limited to the value of the film sold.

Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of the company. The foregoing warranty is exclusive and in lieu of all other warranties, express, implied or statutory, including without limitation any implied warranty of merchantability or of fitness for a particular purpose. In no case shall Northern Technologies International Corporation/Zerust® be liable for incidental or consequential damages. For full warranty and disclaimer information visit, www.zerust.com/warranty.

©2013-2020 Northern Technologies International Corporation (NTIC). All Rights Reserved. NTIC is the owner of the following trademarks: ActivPak®, Cor Tab®, EXCOR®, Flange Saver®, ICT®, NTI®, Plastabs®, Z-CIS®, Zerion®, ZERUST®, 洁乐特 and the Color "Yellow". ABRIGO®, UNICO®, and VALENO® are registered trademarks of EXCOR GmbH, a Joint Venture Partner of NTIC.

Additional Info

Go online to www.zerust.com for product comparisons, application guides, videos and more.

Contact a Zerust® Corrosion Expert

Consult a Zerust® representative to implement an optimum, cost-effective corrosion prevention system across your production facility and supply chain.

Availability

Zerust AxxaClean™ 3048 is sold as a ready to use liquid product.

Part Number Sizes

Immersion
350-M-00021 5, 55 gal

Brush-On
350-M-00022 5, 55 gal

A product of:
Northern Technologies
International Corp
4201 Woodland Road
Circle Pines, MN 55014
USA

Phone. +1 763.225.6600
Fax. +1 763.225.6645
sales@zerust.com
www.zerust.com

